



Borgate Fiorentina

COLORI

colours - couleurs - farbe - ЦВЕТА



Baruffi



Monterinaldi




Falciani



Borgaccio

FORMATI

sizes - formats - format - ФОРМАТЫ



50,2x50,2 (20"x20")



33,3x33,3 (13"x13")



16,5x33,3 (6"x13")



16,5x16,5 (6"x6")



FUGA 3 mm



MODULARITÀ PREVISTA CON FUGA DI 3 MM. NELL'AMBITO DELLO STESSO CALIBRO.
MODULAR LAYING WITH A 3 MM. JOINT WITHIN THE SAME SIZE.
POSE MODULAIRE (OPUS) PREVUE POUR UN JOINT DE 3 MM, MÊME CALIBRE POUR TOUS LES FORMATS POSÉS.
MODULIERTE VERLEGUNG MIT 3 MM. FUGE IN RAHMEN DER GLEICHEN FORMATABMESSUNGEN.
ПРЕДУСМОТРЕННАЯ МОДУЛЬНОСТЬ С ШВОМ 3 MM В РАМКАХ ОДНОГО И ТОГО ЖЕ КАЛИБРА.

Baruffi



50,2x50,2 (20"x20")
6450225 78 ●



33,3x33,3 (13"x13")
6440232 60 ●



16,5x33,3 (6"x13")
6432021 81 ●



16,5x16,5 (6"x6")
6431301 81 ●

Monterinaldi



50,2x50,2 (20"x20")
6450235 78 ●



33,3x33,3 (13"x13")
6440242 60 ●



16,5x33,3 (6"x13")
6432031 81 ●



16,5x16,5 (6"x6")
6431311 81 ●

Falciani



33,3x33,3 (13"x13")
6440212 60 ●



16,5x33,3 (6"x13")
6432001 81 ●



16,5x16,5 (6"x6")
6431281 81 ●

Borgaccio



33,3x33,3 (13"x13")
6440222 60 ●



16,5x33,3 (6"x13")
6432011 81 ●



16,5x16,5 (6"x6")
6431291 81 ●

DECORI decors - decorations - dekore - ДЕКОР


Tappeto



33,3x33,3 (13"x13")
6440661 Baruffi 96 ▲



33,3x33,3 (13"x13")
6440671 Monterinaldi 96 ▲



33,3x33,3 (13"x13")
6440641 Falciani 96 ▲



33,3x33,3 (13"x13")
6440651 Borgaccio 96 ▲

Treccia



8x30 (3,2"x12")
6430411 Grigio 74 ▲

Angolo




8x8 (3,2"x3,2")
6430431 Grigio 55 ▲

PEZZI SPECIALI trims - pieces speciales - formstücke - СОБЫЕЭЛЕМЕНТЫ



Battiscopa
8x33,3 (3,2"x13")
6440689 Falciani
6440691 Borgaccio
6440709 Baruffi
6440719 Monterinaldi
14 ▲ 32 ▢



Angolare con Torello
33,3x33,3 (13"x13")
6440761 Falciani
6440771 Borgaccio
6440781 Baruffi
6440791 Monterinaldi
93 ▲ 2 ▢



Gradone con Torello
33,3x33,3 (13"x13")
6440721 Falciani
6440731 Borgaccio
6440741 Baruffi
6440751 Monterinaldi
66 ▲ 6 ▢

IMBALLI packing - emballages - verpackung - УПАКОВКА

	mm.	PCS / BOX	M2 / BOX	BOX / PLT	M2 / PLT	KG. / PLT
50,2x50,2	9	6	1,51	26	39,26	793
33,3x33,3	8	14	1,55	44	68,2	1100
16,5x33,3	8	16	0,88	68	59,84	1020
16,5x16,5	8	32	0,87	68	59,16	1156

GS		GRES PORCELLANATO SMALTATO GLAZED GRES PORCELAIN GRES CERAME EMAILLE GLASIERTE FEINSTEINZEUG GRES PORCELÁNICO ESMALTADO ГЛАЗУРОВАННЫЙ ФАРФОРОВЫЙ КЕРАМОГРАНИТ		GRUPPO DI APPARTENENZA SECONDO ISO 13006 CLASS GROUPE D'APPARTENANCE ZUGEHÖRIGKEITSGRUPPE GRUPO DE PERTENENCIA ГРУППА ПРИНАДЛЕЖНОСТИ		CE Bla GL	
Simbologia Symbolics Symboles Symbole Simbologias Символы	Caratteristiche Features Caractéristiques Eigenschaften Características Характеристика	Unità di misura Unit of measurement Unité de mesure Masseinheit Unidad de medida Единица измерения	Valore medio Saime Saime mean value Valeur moyenne Saime Durchschnittswert-Saime Valor medio Saime Среднее значение Saime	Valore prescritto Fixed value Valeur prescrite Vorgeschriebener Wert Valor prescrito Требуемое значение	Metodo di prova Test method Méthode d'essai Prüfmethode Método de ensayo Метод испытания		
	Dimensione lati Dimensions-Lenght and widht Dimensions-Longueur et largeur Masse-Länge und Breite Dimensiones-Longitud y ancho Размеры сторон	%	+/- 0,4	+/- 0,6 max	UNI EN ISO 10545-2		
	Rettilineità dei lati Side straightness Rectitude des arêtes Geradlinigkeit der Kanten Rectilíneidad de los lados Прямолинейность сторон	%	+/- 0,4	+/- 0,5 max	UNI EN ISO 10545-2		
	Ortogonalità degli spigoli Corner squariness Angularité Rechtwinkligkeit der Kanten Ortogonalidad de las esquinas Ортогональность кромок	%	+/- 0,4	+/- 0,6 max	UNI EN ISO 10545-2		
	Planarità Flatness - Planéité Ebenfächigkeit - Planeidad Плоскостность	%	+/- 0,4	+/- 0,5 max	UNI EN ISO 10545-2		
	Spessore Thickness - Epaisseur Dicke - Grosor Толщина	%	+/- 5,0	+/- 5,0 max	UNI EN ISO 10545-2		
	Assorbimento d'acqua Water absorption - Absorption d'eau Wasseraufnahme - Absorción de agua Водопоглощение	%	< 0,4	≤ 0,5	UNI EN ISO 10545-3		
	Storzo di rottura Breaking strenght Contrainte de rupture Bruchkraft Esfuerzo de rotura Разрушающее усилие	N	> 1500	≥ 1300 se Spess. ≥ 7,5 ≥ 700 se Spess. ≤ 7,5	UNI EN ISO 10545-4		
	Modulo di rottura Modulus of rupture Coefficient de rupture Bruchmodul Módulo de rotura Модуль разрыва	N/mm²	> 38	≥ 35	UNI EN ISO 10545-4		
	Resistenza all'abrasione Resistance to abrasion Résistance à l'abrasion Beständigkeit gegen Oberflächenverschleiß Resistencia a la abrasión Сопротивление истиранию	-	secondo la serie	Classe 1-5	UNI EN ISO 10545-7		
	Dilatazione termica lineare Coeff. of linear thermal expansion Coeff. d'extension thermique linéaire Linearer Wärmeausdehnungs-Koeffizient Coefficiente de dilatación térmica lineal Линейное тепловое расширение	°MK (-1)	7,0	metodo disponibile available method méthode disponible verfügbare methode método disponible требуемое значение	UNI EN ISO 10545-8		
	Resistenza agli sbalzi termici Thermal shock resistyance Résistance aux chocs thermiques Temperaturwechsel Beständigkeit Resistencia a choque térmico Стойкость к перепадам температуры	-	resiste résiste widerstandsfähig resiste стойкий	metodo disponibile available method méthode disponible verfügbare methode método disponible требуемое значение	UNI EN ISO 10545-9		
	Resistenza alle macchie Stain resistance - Résistance au tâches Flecken Beständigkeit - Resistencia a las manchas Стойкость к образованию пятен	-	≥ 3	3 MIN	UNI EN ISO 10545-14		
	Resistenza ai prodotti chimici di uso domestico Resistance to chemical products Résistance aux produits chimiques Beständigkeit gegen Chemikalien Resistencia a los productos químicos Стойкость к бытовым химикатам	-	conforme conform conforme gleichmässig conforme соответствует	MIN GB	UNI EN ISO 10545-13		
	Resistenza agli acidi e alle basi a bassa concentrazione Resistant to acids and low concentration bases Résistance aux acides et aux bases à faible concentration Widerstandsfähig gegenüber niedrig konzentrierten Säuren und Laugen Resistencia a los ácidos y las bases de baja concentración Стойкость к низким концентрациям кислот и щелочей	-	MIN GLB	secondo classificazione prodotto according to product classification selon classification produit Gemäß Produktklassifizierung СООПАСНО КЛАССИФИКАЦИИ ПРОДУКЦИИ	UNI EN ISO 10545-13		
	Resistenza al gelo Frost resistance Résistance au gel Frostbeständigkeit Resistencia al hielo Морозостойкость	-	resiste résiste widerstandsfähig resiste стойкий	richiesta request demande anfrage solicitud требуемое значение	UNI EN ISO 10545-12		
	Stabilità dei colori Colour stability Stabilité des coloris Lichtechtheit der Färbung Estabilidad de los colores Цветостойкость	-	stabile stable stable stabil estable стойкий	metodo disponibile available method méthode disponible verfügbare methode método disponible требуемое значение	DIN 51094		
	E' a disposizione della gentile clientela la lista dei nostri articoli certificati dall'ente UNI CERTIQUALITY The list of our items certified by "UNI" is available for our customers Pour tous nos clients est disponible la liste de nos produits avec la certification UNI Den Kunden steht eine Aufstellung zur Veruegung der Artikeln die mit UNI Zertifikat bescheinigt wurden La lista de nuestros artículos certificados por el Instituto UNI está a disposición de la estimada clientela. Мы можем предоставить в распоряжении наших заказчиков перечень нашей продукции, сертифицированной органом UNI						